



Showroom & Customer Service

Electric Grey



MBEG / .12424UPS
24 x 24

Galactic Black



MBGB / .12424UPS
24 x 24

Blissful Oak



AV353.10636UPS
6 x 36

Shop & Service Areas

Crossville Cross-Color Mingles



A880 > Onyx 8 x 8



R001 > Grey Mingle 8 x 8

Account Manager

Michael Downes
michael.downes@ahfproducts.com

For pricing and order fulfillment, please contact:

Toni Hale
thale@crossvilleinc.com



Showroom and Customer Service

Technical Specifications

Electric Grey



Sizes & Finishes

Nominal (in)	Actual (mm)	Thickness (mm)	Finish	Application
24 x 24	597 x 597	9.5	UPS	Showroom Tile

Crossville® recommends a minimum grout joint of 3mm. Actual measurements stated in inches indicate tile is calibrated (non-rectified). Actual measurements stated in mm indicate tile is rectified.

Product Performance

Breaking Strength	>450 lbf	ASTM C648
Bond Strength	>200 psi	ASTM C482
Chemical Resistance	Unaffected	ASTM C650
Frost Resistance	Resistant	ASTM C1026
Water Absorption	<0.20%	ASTM C373
Scratch Hardness	7	Mohs Scale

Wet Dynamic COF

UPS	> 0.42	DCOF AcuTest™
-----	--------	---------------

Shade & Texture Index

Electric Grey has a shade variation of V3.



This porcelain tile product is produced with a V3 variation. You can expect clearly distinguishable differences in texture and/or pattern within similar colors.

Information listed here is subject to change.

Blissful Oak



Sizes & Finishes

Nominal (in)	Actual (mm)	Thickness (mm)	Finish
6 x 36	147 x 897	10.5	UPS

Note: All field tile is rectified and modular with a minimum 3mm grout joint. Actual measurements stated in inches indicate tile is calibrated (non-rectified). Actual measurements stated in mm indicate tile is rectified.

Product Performance

Breaking Strength	>500 lbf	ASTM C648
Bond Strength	>200 psi	ASTM C482
Chemical Resistance	Unaffected	ASTM C650
Frost Resistance	Resistant	ASTM C1026
Water Absorption	<0.20%	ASTM C373
Scratch Hardness	7	Mohs Scale

Wet Dynamic Coefficient of Friction Range

UPS	0.42 - 0.52	AcuTest sm
-----	-------------	-----------------------

Shade & Texture Index

Blissful Oak has a shade variation of V3.



This porcelain tile product is produced with a V3 variation. Expect that the amount of color and texture on each piece may vary significantly. Inspect the product upon delivery and for best results, blend tile from several cartons during installation.

Galactic Black



Sizes & Finishes

Nominal (in)	Actual (mm)	Thickness (mm)	Finish	Application
24 x 24	597 x 597	9.5	UPS	Showroom Tile

Crossville® recommends a minimum grout joint of 3mm. Actual measurements stated in inches indicate tile is calibrated (non-rectified). Actual measurements stated in mm indicate tile is rectified.

Product Performance

Breaking Strength	>450 lbf	ASTM C648
Bond Strength	>200 psi	ASTM C482
Chemical Resistance	Unaffected	ASTM C650
Frost Resistance	Resistant	ASTM C1026
Water Absorption	<0.20%	ASTM C373
Scratch Hardness	7	Mohs Scale

Wet Dynamic COF

UPS	> 0.42	DCOF AcuTest™
-----	--------	---------------

Shade & Texture Index

Galactic Black has a shade variation of V3.



This porcelain tile product is produced with a V3 variation. You can expect clearly distinguishable differences in texture and/or pattern within similar colors.

Information listed here is subject to change.

Account Managers

Michael Downes
michael.downes@ahfproducts.com

For pricing and order fulfillment, please contact:

Toni Hale
toni.hale@ahfproducts.com



Shop & Service Areas

Technical Specifications

Crossville Cross-Color Mingles

Porcelain Stone®

Sizes



Sizes & Finishes

Field Tile - Calibrated

Nominal (in)	Actual (in)	Thickness (in)	Grout Joint (in)	Finish
8 x 8	7-3/4 x 7-3/4	5/16	3/16	UPS/CTS
12 x 12	11-3/4 x 11-3/4	5/16	3/16	UPS

This tile is calibrated (non-rectified)
Crossville recommends a minimum 3/16" grout joint.



Product Performance

Breaking Strength	≥300 lbf	ASTM C648
Bond Strength	>200 psi	ASTM C482
Chemical Resistance	Unaffected	ASTM C650
Frost Resistance	Resistant	ASTM C1026
Water Absorption	<0.20%	ASTM C373
Scratch Hardness		Mohs Scale
UPS, CS, CT	7	
PO	7	

Wet Dynamic Coefficient of Friction Range


Unpolished (UPS)	0.50 - 0.60	ANSI A326.3
Cross-Tread (CTS)*	0.50 - 0.60	ANSI A326.3

* The increased real world traction of these types of surfaces cannot be fully realized by any current COF testing methodologies due to their exaggerated facial structure.

** Due to the heavily texture surface DCOF value is not able to be measured by testing device.

Shade & Texture Index

Cross-Colors Mingles has a shade variation of V1.



V1 Uniform appearance

V2 Slight Variation

V3 Moderate Variation

V4 Substantial Variation

Differences among pieces from the same production run are minimal.

Account Managers

Michael Downes
michael.downes@ahfproducts.com

For pricing and order fulfillment, please contact:

Toni Hale
toni.hale@ahfproducts.com